

TECHNICAL SHEET



ORCHESTRA MAX

Solar protection

CHARACTERISTICS	VALUES		UNITS	STANDARDS
	WARP	WEFT		

OVERALL CHARACTERISTICS

Composition	100% solution dyed acrylic Sunacryl			
Finish	Permaclean special self-cleaning and water-resistant treatment. Waterproof and UV resistant acrylic coating on 1 side.			
Weave	Canvas			ISO 7211-1
Weight	320		g/m ²	ISO 2286-1
Width	120		cm	EN 1773
Thickness	0.7		mm	ISO 2286-3
Rigidity	950	680	mN	ISO 2493

FABRIC STRENGTH

Oil-repellent properties	5		class /8	ISO 14419
Tensile strength	154	105	daN	ISO 13934-1
Loss of pressure	< 20	< 20	%	ISO 13561
Variation of the length under load	< 12	< 41	mm	ISO 13561
Length after unloading	< 1	< 16	mm	ISO 13561
Dimensional stability	-3 ; +1	-1; +1	%	ISO 13561
Tear strength	3	2	daN	ISO 13937-1
Elongation at break	37	32	%	ISO 13934-1
Schmerber	1200		mm	ISO 811
Schmerber decrease	< 15		%	ISO 13561
Spray test	5		class /5	ISO 4920
Xenotest 1000h	4		class /5	ISO 105 B04

COLOUR RESISTANCE

Colour fastness UV	7-8		class /8	ISO 105 B02
Colour fastness weather condition	4-5		class /5	ISO 105 B04
Colour fastness under dry friction	5		class /5	ISO 105X12
Colour fastness under wet friction	5		class /5	ISO 105X12

USE

Roll length	60	Im	
Recommended use	Awnings of all types with a strong water resistance		
Guarantee	10	Years	

The values for this product may have a variation of +/-5%.

Comment on the use and making-up of the canvas : the coated side should be used at the underside of the awning

Dickson - Constant

10, rue des Châteaux - BP 109 - Z.I la Pilaterie 59443 Wasquehal cedex - France

Tél. : +33.(0)3.20.45.59.59 - Fax : +33.(0)3.20.45.59.00 - www.dickson-constant.com

SUNACRYL[®]
OUTDOOR FIBRE
by DICKSON[®]

PERMACLEAN
SELF-CLEANING TREATMENT
by DICKSON[®]



WARRANTY
10
YEARS

WARRANTY
MASS
DYED
COLOURS

MADE IN
 FRANCE